

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08G 59/68, 65/04	A1	(11) International Publication Number: WO 94/03519 (43) International Publication Date: 17 February 1994 (17.02.94)
(21) International Application Number: PCT/US93/06649 (22) International Filing Date: 15 July 1993 (15.07.93) (30) Priority data: 923,647 3 August 1992 (03.08.92) US (71) Applicant: OLIN CORPORATION [US/US]; 350 Knotter Drive, P.O. Box 586, Cheshire, CT 06410-0586 (US). (72) Inventors: REISCH, John, W. ; 52 White Birch Drive, Guilford, CT 06437 (US). CAPONE, Deborah, M. ; 311 North Madison Road, Guilford, CT 06437 (US). BLACKWELL, Ronald, S. ; 25 Webb Street, Waterbury, CT 06704 (US).		(74) Agent: CARLSON, Dale, Lynn; Wiggin & Dana, One Century Tower, New Haven, CT 06508-1832 (US). (81) Designated States: AU, BB, BG, BR, CA, CZ, FI, HU, JP, KP, KR, KZ, LK, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SK, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>With amended claims and statement.</i>
(54) Title: POLYOLS HAVING ENHANCED REACTIVITY (57) Abstract The present invention relates to a process for improving the polyurethane-forming reactivity of a propylene oxide-based ethylene oxide-free polyol produced using a double metal cyanide complex catalyst by incorporating therein a minor amount of a base prior to employing the polyol in a polyurethane-forming reaction. Also claimed is the base-containing polyol composition produced in accordance with the present invention.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TC	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

POLYOLS HAVING ENHANCED REACTIVITY

This invention relates generally to polyols produced using double metal cyanide complex catalysts and, more specifically, to a process for improving the reactivity of double metal cyanide complex catalyzed
5 polyols.

The use of double metal cyanide complex ("DMC") catalysts in the preparation of polyols having low ethylenic unsaturation is well-established in the art, as illustrated, for example, by U.S. Patent 3,829,505.
10 The polyols prepared using these catalysts can be fabricated to have a higher molecular weight and/or a lower amount of end group unsaturation than can be prepared using commonly-employed potassium hydroxide ("KOH") catalysts. The '505 patent discloses that these
15 high molecular weight polyol products are suitably reacted with polyisocyanates to prepare rigid or flexible polyurethanes.

Unfortunately, it has now been found by the present inventors that, when utilizing polyols other
20 than ethylene oxide ("EO")-capped polyols, the reactivity of the polyols made with DMC catalysts is less than otherwise might be desired in the subsequent reaction of the polyol with an isocyanate to produce a polyurethane.

25 A solution to this problem of less-than-desired reactivity would be highly desired by the DMC-catalyzed polyol manufacturing community. The present invention provides one solution to this problem.

-2-

In one aspect, the present invention relates to a process for enhancing the reactivity of a polyol produced using a double metal cyanide catalyst which comprises contacting said polyol with at least a trace
5 amount of a base (preferably an alkali metal hydroxide, alkali metal alkoxide, alkaline earth metal hydroxide, alkaline earth metal alkoxide, or a combination thereof), said polyol being free of ethylene oxide capping.

In another aspect, the present invention relates
10 to a process for producing a polyol characterized by enhanced reactivity toward polyisocyanates which comprises the steps of:

(a) forming a polyol having a backbone comprising moieties selected from the group comprising
15 ethylene oxide, propylene oxide, and combinations thereof, said polyol being free of ethylene oxide capping;

(b) contacting said polyol with at least a trace amount of a base in order to provide a
20 base-containing polyol characterized by enhanced reactivity toward polyisocyanates.

In yet another aspect, the present invention relates to a base-containing polyol product comprising a polyol made by double metal cyanide catalysis and having
25 a equivalent weight of at least about 500 (advantageously at least about 1,000, more advantageously at least about 1,500) and a level of end group ethylenic unsaturation of no greater than 0.04 (preferably less than 0.02, more preferably less than
30 0.01) milliequivalents per gram of polyol and at least a trace amount of a base in order to provide a base-containing polyol characterized by enhanced reactivity toward polyisocyanates, said polyol being free of ethylene oxide capping.

-3-

These and other aspects will become apparent upon reading the following detailed description of the invention.

It has now been surprisingly found that the reactivity of polyols made using a DMC catalyst toward polyols is significantly improved by incorporation of at least a trace amount of base into the polyol prior to the reaction of the polyol with a polyisocyanate to form a polyurethane. The resulting polyurethanes exhibit improved physical properties, e.g., improved tensile strength, elongation and/or tear strength, as compared to polyurethanes prepared using a DMC catalyst but not containing at least a trace amount of the base, as demonstrated by the working examples provided hereinbelow.

The DMC catalyst-prepared polyols of the present invention contain at least a trace amount of base, most preferably KOH or NaOH although other bases such as other alkali metal hydroxides, alkaline earth metal hydroxides, alkali metal alkoxides, alkaline earth metal alkoxides, and combinations thereof are also suitably employed. By "at least a trace amount of base" is meant at least 0.5 part per million ("ppm"), preferably at least 1.0 ppm, most preferably at least 1.5 ppm, of the base based upon the weight of the polyol. It is preferred that the amount of the base not exceed 10 ppm (more preferably not more than 5 ppm) based upon the weight of the polyol. The base-containing polyols of the present invention are particularly useful in the production of polyurethane sealants and elastomers, including thermoplastic and thermoset elastomers, as well as cast elastomers, although they also are suitably utilized in the production of polyurethane adhesives, coatings and foams as may be desired.

-4-

The polyurethanes made using the base-containing polyols of the present invention may be made by the prepolymer process or the one-shot process. The polyurethane isocyanate-terminated prepolymer that is
5 utilized when employing the prepolymer process is prepared by reacting an organic polyisocyanate with a polyalkylene ether polyol(s) in an equivalent ratio of NCO to OH groups of from about 1.02/1 to about 15/1, using standard procedures, to yield an isocyanate-
10 terminated prepolymer of controlled molecular weight. Preferably, the NCO/OH ratio ranges from about 1.3/1 to about 5/1. The reaction may be accelerated by employing a catalyst; common urethane catalysts are well known in the art and include numerous organometallic compounds as
15 well as amines, e.g., tertiary amines and metal compounds such as lead octoates, mercuric succinates, stannous octoate or dibutyltin dilaurate may be used. Any catalytic amount may be employed; illustratively, such amount varies, depending on the particular catalyst
20 utilized, from about 0.01 to about 1 percent by weight of the polyurethane prepolymer.

Preferred base-containing polyols within the scope of the present invention are the polyether diols and the polyether triols, and combinations thereof.
25 Suitable polyether triols include various polyoxyalkylene polyols and mixtures thereof. These can be prepared, according to well-known methods, by condensing an alkylene oxide, or a mixture of alkylene oxides using random or step-wise addition, with a
30 polyhydric initiator or mixture of initiators. Illustrative alkylene oxides include ethylene oxide, propylene oxide, butylene oxide, amylene oxide, aralkylene oxides such as styrene oxide, and the halogenated alkylene oxides such as trichlorobutylene

oxide and so forth. The most preferred alkylene oxide is propylene oxide or a mixture thereof with ethylene oxide using random or step-wise oxyalkylation.

The polyhydric initiator used in preparing the
5 polyether triol reactant includes the following and mixtures thereof: the aliphatic triols such as glycerol, propoxylated glycerol adducts, trimethylolpropane, triethylolpropane, trimethylolhexane, and the like.

10 A preferred group of polyhydric initiators for use in preparing the polyether triol reactant is one which comprises triols such as glycerol, propoxylated glycerol adducts, trimethylolpropane and the like.

The polyether diols are prepared by an analogous
15 reaction of alkylene oxide, or mixture of alkylene oxides with a polyhydric initiator. In this case the initiator is a diol such as ethylene glycol, 1,3-propylene glycol, dipropylene glycol, butylene glycols, butane diols, pentane diols, and the like.


20 A preferred group of polyhydric initiators for use in preparing the polyether diol reactant is one which comprises diols such as ethylene glycol, diethylene glycols, propylene glycol, dipropylene glycol, or water.

25 The alkylene oxide-polyhydric initiator condensation reaction is preferably carried out in the presence of a double metal cyanide catalyst. The use of a double metal cyanide catalyst rather than a base such as KOH during the preparation of the polyol provides
30 distinct advantages in regard to the end group unsaturation level of the polyol produced. Without wishing to be bound by any particular theory, it is speculated by the present inventor that unsaturated end groups result in monofunctional species that act as

chain stoppers in elastomer formation. In polyol synthesis with KOH catalysis the unsaturation formed increases as a direct function of equivalent weight. Eventually conditions are established wherein further
5 propylene oxide addition fails to increase the molecular weight. In other words the use of alkali catalysts to produce high molecular weight, hydroxy terminated polyoxypropylene ethers results in a substantial loss in hydroxy functionality. With double metal cyanide
10 catalysis much less unsaturation is formed allowing higher equivalent weight polyols to be prepared.

The double metal cyanide complex class catalysts suitable for use and their preparation are described in U.S. Pat. Nos. 4,472,560 and 4,477,589 to Shell Chemical
15 Company and U.S. Pat. Nos. 3,941,849; 4,242,490 and 4,335,188 to The General Tire & Rubber Company.

One double metal cyanide complex catalyst found particularly suitable for use is a zinc hexacyanometallate of formula:



wherein M may be Co(III), or Cr(III) or Fe(II) or Fe(III); x, y, and z may be fractional numbers, integers, or zero and vary depending on the exact method of preparation of the complex.

25 In producing a polyurethane utilizing the base-containing polyols of the present invention, any suitable organic polyisocyanate, or mixture of polyisocyanates, may be used. Illustrative are toluene diisocyanate, such as the 80:20 and the 65:35 mixtures
30 of the 2,4- and 2,6-isomers, ethylene diisocyanate, propylene diisocyanate, methylene-bis (4-phenyl) isocyanate (also referred to as diphenylmethane

-7-

diisocyanate or MDI), xylene diisocyanate (XDI), isophorone diisocyanate (IPDI), 3,3'-bistoluene-4,4'-diisocyanate, hexamethylene diisocyanate (HDI), hydrogenated MDI, hydrogenated XDI, and modified liquid MDI adducts such as carbodiimide-modified MDI, naphthalene-1,5-diisocyanate, the polymeric isocyanates such as polyphenylene polymethylene isocyanate (PMDI), mixtures and derivatives thereof, and the like. In accordance with a particularly preferred embodiment of the invention, there is employed an isomeric mixture of 2,4- and 2,6-toluene diisocyanate in which the weight ratio of the 2,4-isomer to the 2,6-isomer is from about 60:40 to about 90:10, and more preferably from about 65:35 to about 80:20, as well as MDI.

Chain extenders which can be utilized in preparing polyurethanes, particularly coatings, sealants, adhesives and elastomers, utilizing the base-containing polyols of the present invention include diols and diamines such as 4,4'-methylene bis(2-chloroaniline) ("MOCA"), butane diol, hexane diol, propylene glycol, bisphenol A, or polyalkylene oxide polyols with molecular weights between 100 - 2,000, or the prepolymer can be moisture cured with water. The chain extenders can also be triols such as glycerine, trimethylol propane, or propoxylated adducts of glycerine or trimethylol propane or amines like diethyltoluene diamine, ethylene diamine, substituted aromatic diamines such as the product commercially available as UNILINK 4200, a product of UOP, Inc, triisopropyl amine, methylene bis(ortho-chloro-aniline), N,N-bis(2-hydroxypropyl)-aniline which is commercially available as ISONOL 100, a product of Dow Chemical Corp., and the like, and combinations thereof.

-8-

Preferred chain extenders include MOCA, butane diol, trimethylol propane, diethyltoluene diamine, N,N-bis(2-hydroxypropyl)-aniline, and combinations thereof. The chain extension can be conducted either in situ during the prepolymer formation or in a separate reaction step.

In preparing the polyurethanes utilizing the base-containing polyols of the present invention, the polyol(s), polyisocyanate(s), chain extender(s), and other components are reacted, typically under conditions of an elevated temperature. Urethane forming catalysts can be used as well as antioxidants or other antidegradants. The urethane-forming components may be mixed with the usual compounding ingredients, e.g. plasticizers, adhesion promoters, fillers and pigments like clay, silica, fumed silica, carbon black, talc, phthalocyanine blue or green, TiO_2 , U-V absorbers, MgCO_3 , CaCO_3 and the like. The compounding ingredients, such as fillers, are suitably employed in the elastomer in an amount of between 0 and about 75 weight percent based upon the weight of the elastomer. The polymerization reaction may be carried out in a single reaction (one-shot process), or in one or more sequential steps (prepolymer process). In the one-shot process, all the isocyanate-reactive components are reacted simultaneously with the polyisocyanate. In such process, it is normal practice to blend all components except the polyisocyanate into a "B-side" mixture, which is then reacted with the polyisocyanate to form the polyurethane and/or polyurea elastomer. However, the order of mixing is not critical as long as the components do not undesirably react before all components are present. The reaction mixture is usually then placed in a mold and cured at a suitable

temperature. The apparatus used for blending and molding is not especially critical. Hand mixing, conventional machine mixing, and the so-called reaction injection molding (RIM) equipment are all suitable. In
5 the prepolymer process, all or a portion of one or more of the isocyanate reactive materials is reacted with a stoichiometric excess of the polyisocyanate to form an isocyanate-terminated prepolymer. This prepolymer is then allowed to react with the remaining
10 isocyanate-reactive materials to prepare the polyurethane and/or polyurea elastomer. The prepolymer can be prepared with either the polyether or the chain extender, or a mixture of both.

As used herein, the term "molecular weight" is
15 intended to designate number average molecular weight. The term "equivalent weight" designates the molecular weight divided by the number of hydroxyl groups per molecule of polyol.

While the invention has been described above
20 with reference to specific embodiments thereof, it is apparent that many changes, modifications and variations can be made without departing from the inventive concept disclosed herein. Accordingly, it is intended to embrace all such changes, modifications and variations
25 that fall within the spirit and broad scope of the appended claims.

-10-

EXAMPLE 1

A. Preparation of a Polyol with a
Double Metal Cyanide Catalyst

A propoxylated glycerine precursor 100 g (133.6
5 eq. wt., 0.748 eq.) was added to a 1 liter autoclave.
Zinc hexacyanocolbate (0.1 g) was added and the
autoclave was flushed with nitrogen three times. The
mixture was heated to 100°C. Propylene oxide (30 g) was
added and it reacted as evidenced by a drop in
10 pressure. PO was fed into the reactor at a rate to
maintain the pressure below 30 psi and 609.0 g of
propylene oxide was added within two hours. At this
point 548 g of the mixture was removed to allow space
for more epoxide leaving 162. grams in the reactor. An
15 additional 340 grams of propylene oxide were fed into
the reactor over a period of 1.5 hours to produce a
polyol with a molecular weight of 10,000, hydroxyl
number 16.8. Using a similar procedure, polyols with
hydroxyl numbers between 16 and 60 were prepared. Diols
20 were prepared by starting with dipropylene glycol based
precursors instead of glycerine based precursors.

B. Polyol Treatment with Hydrogen Peroxide
to Remove the DMC Catalyst Using the
Process Described in U.S. Patent 5,099,075

25 A polyol (500.0 g) prepared as described in
Example 1A containing residual DMC catalyst was heated
to 100°C and 30% hydrogen peroxide (3.0g, 0.2 wt.%
peroxide) was added. The mixture was heated at 100°C
for one hour and then Celite (10.0 g, 2 wt.%) was added
30 and the mixture was vacuum stripped for one hour and

-11-

filtered. A clear polyol containing 0 ppm cobalt and 0 ppm zinc was obtained.

EXAMPLE 2

5 Sealants Prepared with DMC Catalyzed Polyol and Adjusted Reactivity DMC Catalyzed Polyol

A. Prepolymer Preparation: TDI-80 22.86 g, 0.262 eq. and a 10,000 molecular weight triol prepared as described in example 1 (270.0 g, OH no. 17.3, 0.0833 eq.) were added to a flask under nitrogen and heated to
10 80°C for 5 hours with stirring. The percentage of free NCO was measured and found to be 2.40%.

B. Sealant Preparation: A prepolymer prepared as described in example 2A (106.0 g, 0.0606 eq.), POLY-G® 20-56 polyol (58.7 g, 1020 eq. wt., 0.0576 eq.,
15 105 index), and dried fibrous talc (40.9 g) were mixed on a high speed mixer for several minutes. The mixture was degassed and T-10 stannous octoate catalyst 0.724 g was added. The mixture was stirred under vacuum for two minutes and then poured between glass plates with a 1/8" spacer and cured at 70°C for 16 hours. The sealant was
20 aged at 20°C and 50% relative humidity for one week before testing.

C. Polyol Reactivity Adjustment: Low levels of KOH (0.935, 1.87, 2.82 ppm) were added to a 10,000 mw
25 triol that was prepared as described in example one. The polyol was vacuum dried at 110°C for 2 hours and then used to prepare sealants as described above in example 2a & b. Properties obtained with the adjusted reactivity polyols and the unadjusted polyol are
30 compared in Table 1 below:

-12-

TABLE I

Two Component Talc Filled Sealants. TDI/10,000 mw Triol Prepolymers 2.4% free NCO. Extended with 2000 mw Diol

KOH added to polyol	T-10 catalyst grams	Modulus	Ult. Tensile	Elongation %	Shore A Hardness
0	0.724	To soft to test			5
0.935 ppm	0.743	77	310	2390	20
1.87 ppm	0.73	50	300	3950	20
2.82 ppm	0.66	164	250	630	40

- 10 The above data show that when no base was added to the polyol a soft sealant (Shore A hardness 5) that was too soft to test was obtained. When small levels of base were added to the polyol sealants with higher hardness (20-40 Shore A) and excellent tensile elongation properties were obtained.

-13-

EXAMPLE 3

Cast Elastomers Prepared with DMC Catalyzed Polyols
and with Adjusted Reactivity DMC Catalyzed Polyols

3A. A 2000 molecular weight diol was prepared
5 with DMC catalyst using a propoxylated dipropylene
glycol precursor using the procedure described in
Example 1a. The polyol was treated with hydrogen
peroxide as described in example 1b and the cobalt and
zinc were completely removed from the polyol.

10 The reactivity of the polyol was adjusted by
adding varying levels of KOH (1.87, 2.81, 3.74 ppm).
The polyols were vacuum dried at 110°C for two hours to
remove water.

3B. Prepolymer preparation: Diphenyl methane
15 diisocyanate (MDI) was melted in an oven at 50°C. The
polyol 400 g, 0.4 eq. were added to a flask under
nitrogen and heated to 60°C. MDI (148.0 g, 1.18 eq.)
was added and the mixture was heated to 80°C for 2.5
hours with stirring under nitrogen. The percentage of
20 free NCO was measured and found to be 6%.

3C. Elastomer Preparation: The prepolymer
described in example 3B above 200 g, 0.286 eq. and dried
butane diol 12.5 g, 0.277 eq., 103 index and Cocure 30
catalyst 0.32 g were mixed on a high speed mixer for
25 15-20 seconds at 3000-4000 rpm. The mixture was
degassed in a vacuum desiccator until the surface was
bubble free. The mixture was poured between glass
plates using a 1/8" spacer and cured in an oven at
100-105°C for 16 hours. The elastomers were aged at 50%
30 relative humidity for one week before testing.

Physical properties of the elastomers obtained
with the adjusted reactivity polyols compared to the
unadjusted polyol are presented in Table 2 below:

TABLE II

Physical Properties of Elastomers Prepared with Adjusted Reactivity DMC Catalyzed Polyols Compared to Unadjusted Polyol. MDI/2000 mw diol prepolymers, 6% free NCO, extended with butane diol.

ppm KOH added	Shore A	100% Modulus	Tensile Strength	Elong. %	Tear Die-C	Comp. Set %
0	70	349	813	479	194	39
1.87	68	353	1684	850	286	38
2.81	68	349	2554	654	245	32

5

The above data showed that small amounts of base added to the double metal cyanide catalyzed polyol dramatically improved the tensile strength, elongation and tear strength of the elastomers.

-15-

While the invention has been described above with references to specific embodiments thereof, it is apparent that many changes, modifications and variations in the materials, arrangements of parts and steps can be
5 made without departing from the inventive concept disclosed herein. Accordingly, the spirit and broad scope of the appended claims is intended to embrace all such changes, modifications and variations that may occur to one of skill in the art upon a reading of the
10 disclosure.

Having thus described the invention, what is claimed is:

WHAT IS CLAIMED IS:

1. A process for enhancing the reactivity of a polyol produced using a double metal cyanide catalyst which is characterized by, after removing any residual
5 double metal cyanide catalyst by treating the polyol with hydrogen peroxide, contacting said polyol with between 0.5 and 10 ppm, based upon the weight of said polyol, of a base selected from the group consisting of an alkali metal hydroxide, alkali metal alkoxide,
10 alkaline earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof, said polyol being free of ethylene oxide capping.
2. The process of claim 1 characterized in that said base is selected from the group consisting of an
15 alkali metal hydroxide, alkali metal alkoxide, alkaline earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof.
3. The process of claim 2 characterized in that said alkali metal is sodium or potassium.
- 20 4. The process of claim 1 characterized in that said trace amount is between 0.5 and 10 ppm of said base.

-17-

5. A process for producing a polyol characterized by enhanced reactivity toward polyisocyanates said process being characterized by the steps of:

- 5 (a) forming a polyol having a backbone comprising moieties selected from the group comprising ethylene oxide, propylene oxide, and combinations thereof, said polyol being produced using a double metal cyanide catalyst and being
10 free of ethylene oxide capping, and removing any residual double metal cyanide catalyst by treating the polyol with hydrogen peroxide;
(b) contacting said polyol with at least a trace
15 amount of a base in order to provide a base-containing polyol characterized by enhanced reactivity toward polyisocyanates.

6. The process of claim 5 characterized in that said base is selected from the group consisting of an alkali metal hydroxide, alkali metal alkoxide, alkaline
20 earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof.

7. The process of claim 6 characterized in that said alkali metal is sodium or potassium.

8. The process of claim 5 characterized in that
25 said trace amount is between 0.5 and 10 ppm of said base.

-18-

9. A base-containing polyol product comprising a polyol product comprising a polyol made by double metal cyanide catalysis and characterized by having an equivalent weight of at least about 500 and a level of end group ethylenic unsaturation of no greater than 0.04 milliequivalents per gram of polyol and at least a trace amount of a base in order to provide a base-containing polyol characterized by enhanced reactivity toward polyisocyanates, said polyol being free of ethylene oxide capping.

10. The composition of claim 9 characterized in that said polyol has a equivalent weight of at least about 1,000.

11. The composition of claim 9 characterized in that said polyol has a equivalent weight of at least about 1,500.

12. The composition of claim 9 characterized in that said polyol has an end group ethylenic unsaturation of less than 0.02 milliequivalents per gram of polyol.

13. The composition of claim 9 characterized in that said polyol has an end group ethylenic unsaturation of less than 0.01 milliequivalents per gram of polyol.

14. The composition of claim 9 characterized in that said base is an alkali metal hydroxide.

-19-

15. The composition of claim 9 characterized in that said base is potassium hydroxide.

16. The composition of claim 6 characterized in that said trace amount is at least 0.5 ppm of said base.

AMENDED CLAIMS

[received by the International Bureau on 9 November 1993 (09.11.93);
original claims 1-16 replaced by amended claims 1-4 (2 pages)]

1. A process for enhancing the reactivity of a polyol produced using a double metal cyanide catalyst which is characterized by, after removing any residual double metal cyanide catalyst by treating the polyol with hydrogen peroxide, contacting said polyol with between 0.5 and 10 ppm, based upon the weight of said polyol, of a base selected from the group consisting of an alkali metal hydroxide, alkali metal alkoxide, alkaline earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof, said polyol being free of ethylene oxide capping.

2. The process of claim 1 characterized in that said base is selected from the group consisting of an alkali metal hydroxide, alkali metal alkoxide, alkaline earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof wherein said alkali metal is sodium or potassium.

3. A process for producing a polyol characterized by enhanced reactivity toward polyisocyanates which comprises the steps of:

(a) forming a polyol having a backbone comprising moieties selected from the group comprising ethylene oxide, propylene oxide, and combinations thereof, said polyol being produced using a double metal cyanide

catalyst and being free of ethylene oxide capping, and removing any residual double metal cyanide catalyst by treating the polyol with hydrogen peroxide;

(b) contacting said polyol with at least a trace amount of a base in order to provide a base-containing polyol characterized by enhanced reactivity toward polyisocyanates.

4. The process of claim 3 characterized in that said base is selected from the group consisting of an alkali metal hydroxide, alkali metal alkoxide, alkaline earth metal hydroxide, alkaline earth metal alkoxide, and combinations thereof, wherein said alkali metal is sodium or potassium.

STATEMENT UNDER ARTICLE 19

In response to the International Search Report mailed 23 September 1993 having a two (2) month period for response set to expire on 23 November 1993, Applicant has submitted replacement claim pages 16 and 17 in the above-referenced International Application. As a result of the amendment, new claims 1 through 4 (which correspond to original claims 1-4) are intended to replace original claims 1 through 16. The limitations of claims 2 and 4 as originally filed, specifying the list of bases and amount of base, have been incorporated into new claims 1 and 3, as further supported by the instant specification at page 3, lines 22-32. In addition, these claims, and the claims dependent therefrom, have now been amended to recite a limitation that any residual double metal cyanide catalyst has been removed prior to contact of the polyol with the base. This limitation is supported by the working examples at page 10, lines 21-31 of the instant specification. Applicant believes that new claims 1-4 more clearly identify the invention and the novelty and inventive step associated with the pending claims.

It is believed that the new claims serve to more clearly delineate the distinctions between the instant invention and the inventions disclosed in the prior art cited in the outstanding Search Report. For example, the cited Harper patent is not suggestive of the polyol reactivity advantages

associated with the addition of base to the polyol after DMC catalyst removal from the polyol has already been effected. In this regard, refer to the physical property data appearing in Table II at page 14 of the instant specification for polyols containing base as compared to a polyol containing no base.

It is believed that the amended claims meet the novelty, industrial applicability and inventive step requirements.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 90/06649

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : C08G 59/68, 65/04

US CL : 528/414, 403, 410; 568/618, 620, 621, 625

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 528/414, 403, 410; 568/618, 620, 621, 625

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

Please See Extra Sheet.

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
<u>X</u> Y	US, A, 4,877,906 (HARPER) 31 OCTOBER 1989. See entire document.	1, 2, 3, 5, 6, 7, <u>9, 14, 15</u> 4, 8, 10-13, 16



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	*T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A document defining the general state of the art which is not considered to be part of particular relevance	*X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E earlier document published on or after the international filing date	*Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*& document member of the same patent family
*O document referring to an oral disclosure, use, exhibition or other means	
*P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

01 SEPTEMBER 1993

Date of mailing of the international search report

23 SEP 1993

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

DUC TRUONG

Telephone No. (703) 308-2351